



HOLOUL FACTORY

FOR CEMENT PRODUCTS

CEMENT BASED PLASTER

www.holoul.com

CEMENT BASED PLASTER PRE-MIX EX1007 P

PRODUCT:

Premix Plaster is a cement based ready mix plaster, to carry out traditional plastering works in a clean and speedy manner, while keeping a homogeneous mix.

It allows better workability and curing.

Due to its content in waterproofing additives, premix fiber is particularly recommended for external uses.

ASSOCIATED FINISHES:

Premix Plaster is particularly recommended for external applications. Associated substrates:

- Concrete blocks, bricks, etc...
- Fair faced concrete
- Prefabricated concrete
- Traditional and spraying cement based plaster

CHARACTERISTICS	
Appearance	Grey powder
M/V of powder	1.39 around
Grain size	0.02 to 1.5 mm
Composition	Portland cement, selected sand, fibers, additives
Wet mix life	< 1 hr
Compressive strength	10 MPa \pm 2
Resistance to fire as per BS EN 1- 998	Class A1



APPLICABLE STANDARDS :

DTU 26.1, DTU 20.1 & 23.1 (substrates). BS 5262: 1991, BS 5492: 1990, BS 4551 part 2: 1998, ASTM C 150, ASTM C 926, ASTM C 897. BS EN 1015-12

INSTRUCTIONS FOR USE

SURFACE PREPARATION:

All substrates must be clean, sound, dust free, and free from all traces of oil and laitance. The traces of mould joints must be levelled.

In case of smooth surfaces, a spatter dash slurry coat should be made as a key, by using premix Plaster coat.

Let it dry 2 days before plastering application. Before application, all surfaces must be dampened.

PRODUCT PREPARATION:

Mix manually or mechanically a 10 kg bag of premix Plaster to 1.5 to 2 lit. clean water until homogeneous paste is obtained. Leave the mix a few minutes.

PRODUCT APPLICATION:

The plastering is applied manually with a plastering trowel, or splashing plastering machine until 1.5 cm thickness per coat.

After levelling, let the product dry before finishing it with a synthetic sponge.

CURING:

Protect the newly applied plaster from sunshine and wind. The new plaster has to be cured with water for at least three days by spraying 3 to 4 times daily.

YIELD:

Around 2 kg per m² per 1 mm thickness.

STORAGE:

12 months after manufacturing date in original and non-open packaging, under cover, in dry condition, away from humidity, protected from extreme temperatures and direct sunlight.



📍 Jeddah, Saudi Arabia
P.O.Box: 0000,
📞 888 77 66 055
☎ 555 44 33 012
✉ info@holoul.com

